



Product Specification GranuBent PORE-TEC

CAS – Number: 1302 – 78 – 9
 Description: Sodiu**m**ben**to**nite, granulated with PORE-TE**C**hnology
 Composition: 100 % Bentonite

Parameter	Conforming values	Non-conforming
Appearance	whitish	Not corresponding
Odour	Neutral	Not corresponding
Moisture	≤ 12 %	> 12 %
pH-Value	9.0 – 10.5	< 9.0 / > 10.5
<u>Soluble matter in 1% tartaric acid (German Wine law)</u>		
Soluble sodium	1.1 – 1.4 %	< 1.1 % / > 1.4 %
Soluble calcium	≤ 0.40 %	> 0.40 %
Soluble iron	≤ 0.05 %	> 0.05 %
<u>Soluble matter in 0.5% tartaric acid (OIV)</u>		
Soluble arsen	≤ 2 ppm	> 2 ppm
Soluble lead	≤ 5 ppm	> 5 ppm

Values for information purposes according to OIV codex		
Montmorillonite content	≥ 80 %	
Presence of large particels	< 8 g / 100 g	
De-acidification test trials	< 2.5 Eq/kg	
<u>Components soluble in 0.5% tartaric acid, pH 3, OIV</u>		
Sodium:	≤ 1,0 %	
Calcium + Magnesium	≤ 100 meq/100g	
Mercury	≤ 1 ppm	
Iron:	< 0.06 %	
Aluminium	< 2,5 g/kg	

Bentonite is admitted in the European Union according to EU regulation 934/2019 and EU guideline 2012/12 as a processing aid for the treatment of wine and fruitjuices. The product in its purity and composition corresponds to the OIV Resolution 11/2003.

User must check compliance with national regulations.

ERBSLÖH Geisenheim GmbH
 Erbslöhstraße 1, 65366 Geisenheim, Germany
 Tel: +49 6722 708-0, Fax: +49 6722 6098, info@erbsloeh.com, www.erbsloeh.com